



From the Sacred Land of Palestine
".to CNC-Crafted Stone Excellence

☎ 00972527057642
☎ 00972599340613
✉ info@alshahama.ps



A12

Tafooh Fateha



Water Absorption %	0.71
Specific Gravity	2.642
Compressive Strength (Dry), Mpa	103.8
Compressive Strength (Wet), Mpa	90
Flexural Strength (MPa)	8.33
Groove Length (mm)	22.7



A30

Marawi Karim




Water Absorption %	2.95
Specific Gravity	2.467
Compressive Strength (Dry), Mpa	104.2
Compressive Strength (Wet), Mpa	61.9
Flexural Strength (MPa)	9
Groove Length (mm)	24.3



A31

White Sheikhs



Water Absorption %	0.9
Specific Gravity	2.613
Compressive Strength (Dry), Mpa	133.7
Compressive Strength (Wet), Mpa	112.1
Flexural Strength (MPa)	7.77
Groove Length (mm)	22.4

A51

Tfooh Wasta



Water Absorption %	1.87
Specific Gravity	2.477
Compressive Strength (Dry), Mpa	132
Compressive Strength (Wet), Mpa	106.3
Flexural Strength (MPa)	6.89
Groove Length (mm)	22.4



A32

Galilee GRAY



Water Absorption %	2.38
Specific Gravity	2.473
Compressive Strength (Dry), Mpa	93.7
Compressive Strength (Wet), Mpa	92.5
Flexural Strength (MPa)	11.83
Groove Length (mm)	23.6



A33

White Sheikhs



Water Absorption %	0.77
Specific Gravity	2.623
Compressive Strength (Dry), Mpa	123.8
Compressive Strength (Wet), Mpa	115.3
Flexural Strength (MPa)	7.35
Groove Length (mm)	23.8

A34 Birzeit



Water Absorption %	0.47
Specific Gravity	2.649
Compressive Strength (Dry), Mpa	112.2
Compressive Strength (Wet), Mpa	104
Flexural Strength (MPa)	7.03
Groove Length (mm)	18.2

A16

jild el Nimer Shyoukh



Water Absorption %	0.9
Specific Gravity	2.6
Compressive Strength (Dry), Mpa	116.2
Compressive Strength (Wet), Mpa	82.8
Flexural Strength (MPa)	7.2
Groove Length (mm)	20.7

A51

Tfooh Wasta



Water Absorption %	1.87
Specific Gravity	2.477
Compressive Strength (Dry), Mpa	132
Compressive Strength (Wet), Mpa	106.3
Flexural Strength (MPa)	6.89
Groove Length (mm)	22.4

A35

Yatta Karimi



Water Absorption %	0.3
Specific Gravity	2.664
Compressive Strength (Dry), Mpa	112.2
Compressive Strength (Wet), Mpa	96.6
Flexural Strength (MPa)	8.07
Groove Length (mm)	23.8



A36

Bani Na'im



Water Absorption %	0.86
Specific Gravity	2.618
Compressive Strength (Dry), Mpa	97.1
Compressive Strength (Wet), Mpa	69.7
Flexural Strength (MPa)	10.32
Groove Length (mm)	20.6

A37

Bani Na'im



Water Absorption %	1
Specific Gravity	2.615
Compressive Strength (Dry), Mpa	76.5
Compressive Strength (Wet), Mpa	59
Flexural Strength (MPa)	7.12
Groove Length (mm)	23.4



A52

Shyoukh Sabaeeniyeh



Water Absorption %	2.02
Specific Gravity	2.475
Compressive Strength (Dry), Mpa	149.8
Compressive Strength (Wet), Mpa	110.2
Flexural Strength (MPa)	10.38
Groove Length (mm)	22.3



PALESTINIAN STONE — SCULPTED IDENTITY,
PRESERVED HERITAGE, TIMELESS ELEGANCE.

من نحن

في شركة الشاهامة للحجر، نطلق من قلب فلسطين، من أرض تنبض بالتاريخ والقداسة، لنحوّل الحجر الفلسطيني الأصيل إلى حلول معمارية معاصرة تجمع بين الأصالة والابتكار.

نستند إلى خبرة متراكمة، مدعومة بأحدث تقنيات القص والتشكيل باستخدام لنقّدم أعمالاً حجرية تتسم بالقوة، والدقة، والجمال، وتلبي متطلبات CNC، العمارة الحديثة بمعايير عالمية.

نحن لا نعمل بالحجر فقط، بل نُجسّد هوية، ونحفظ إرثاً، ونصنع تفاصيل تربط الماضي العريق بحاضر متطور ومستقبل واعد.



OUR PROJECTS



أنواع تشطيبات الحجر

نوفر مجموعة متنوعة من تشطيبات الحجر التي تلبي المتطلبات الجمالية والمعمارية المختلفة، باستخدام تقنيات حديثة وأعمال يدوية دقيقة



Polished



Honed



Brushed



Bush Hammered



Rough bush Hammered



Sandblasted



Leather



Flamed



Light Grooving



Antique



Tobbzeh



Scratchrd



Light Chiseled



Rough Chiseled



Natural Split Face



Rough Chiseled

منشآتنا


تمتلك شركة الشهامة للحجر منشآت إنتاج متطورة ومجهزة بما يضمن جودة CNC بأحدث خطوط القص والتشكيل وتقنيات عالية، دقة في التفاصيل، وقدرة على تنفيذ المشاريع الكبيرة وفق أعلى المعايير







شركة الشاهامة للتعهدات والتجارة م. خ. م.



AL-SHAHAMA FOR MARBLE Co.

**From the Sacred Land of Palestine
".to CNC-Crafted Stone Excellence**



☎ 00972527057642

☎ 00972599340613

✉ info@alshahama.ps